





Super Prime

Boards are graded on both faces. On principle it is a 4 sides clear material where abt. 80% of the boards in a pack are 4 sc and abt. 20% are having a defect on one side or minor defects on both sides. There could be trace of sap on the edges. Tiny pin knots could be found.

THICKNESS 27 mm, 33/34 mm, 40 mm, 52 mm, 65 mm, 80 mm, 102 mm, 120 mm

WIDTHS 12 cm and wider allowing 10-11 cm

24 cm and wider

LENGTHS 1.00 mt to 1.70 mt

1.80 mt to 2.00 mt 2.10 mt and longer up to 3.50 mt 3.60 mt to 3.90 mt

4.00 mt and longer







SP 1

Front face

Back face

Back face



SP 2

Front face

| The state of the

SP3

Front face

SP 4

Pri-Fas

Boards are graded on both faces. This is material that doesn't make Super Prime. It is mostly a three side clean material, there are also four side clean boards having only hair checks on one face of the boards and occasional two side clean boards. The two side clean boards are usually good boards having a single knot passing through and through. There could be trace of sap on the edges. Tiny pin knots could be found. This is our competitors PRIME in general. It is a good grade for customers that are more keen on prices.

THICKNESS	27 mm, 33/34 mm, 40mm, 52mm, 65 mm, 80 mm, 102 mm, 120 mm
WIDTHS	12 cm and wider allowing 10-11 cm
LENGTHS	1.80 mt and longer



PF 1

Front face



Back face



PF 2

Front face



Back face



PF 3

Front face



Back face



PF 4

Front face



Back face



Natural

Boards are graded on both faces. Knots with no limitation in dimension in principle one per linear metre. Tiny pin knots could be found. Typical grade for furniture companies, panels and flooring producers. There could be trace of sap on the edges. In its average it has a defect per each metre.

THICKNESS 27 mm, 33/34 mm, 40 mm, 52 mm, 65 mm, 80 mm, 102 mm, 120 mm

(When S2S) 27(23,8) mm, 33(29,5) mm, 40(36,0) mm, 52(48,5) mm

WIDTHS 12 cm and wider allowing 10-11 cm 24 cm and wider

LENGTHS 1.80 mt and longer

We produce this items also S2S pre-planed for companies that are using scanners to optimize (rip and/or cross cut) the boards and they prefer and need to have the wood pre-planed (clear from water stains or sticker marks). We are grading the material after the plaining. When S2S is very flat and straight.







S2S

NAT 1

Front face



Back face



NAT 2

Front face



Back face



NAT 3

Front face



Back face



NAT 4

Front face



Back face



Rustic

Boards are graded on both faces. Sound knots admitted with no limitation, eventual unsound knots maximum one per linear metre. There could be trace of sap on the edges, trace of heart is also allowed.

THICKNESS 27 mm, 33/34 mm, 40 mm, 52 mm, 65 mm, 80 mm, 102 mm, 120 mm

(When S2S) 27(23,8) mm, 33(29,5) mm, 40(36,0) mm, 52(48,5) mm

WIDTHS 12 cm and wider allowing 10-11 cm 24 cm and wider

LENGTHS 1.80 mt and longer

We produce this items also S2S pre-planed for companies that are using scanners to optimize (rip and/or cross cut) the boards and they prefer and need to have the wood pre-planed (clear from water stains or sticker marks). We are grading the material after the plaining. When S2S is very flat and straight.







RUS₁



Back face



RUS 2

Front face



Back face



RUS 3

Front face



Back face



RUS 4

Front face



Back face




S2S

SAP1F

Boards are graded on both faces. These are side boards having one sappy face. I face is like the Super Prime, almost all clean from defects the reverse side is having sap.

THICKNESS	27 mm
WIDTHS	12 cm and wider allowing 10-11 cm
LENGTHS	1.80 mt and longer



SAP 4

Front face

Back face



Front faces

		THICKNESS 27 mm 33/34 mm 40 mm 52 mm 65 mm 80 mm 102 mm 120 mm	WIDTHS 12 cm and wider allowing 10-11 cm 24 cm and wider	1.00 mt to 1.70 mt 1.80 mt to 2.00 mt 2.10 mt and longer up to 3.50 mt 3.60 mt to 3.90 mt 4.00 mt and longer
Front faces	Back faces	THICKNESS 27 mm 33/34 mm 40 mm 52 mm 65 mm 80 mm 102 mm	WIDTHS 12 cm and wider allowing 10-11 cm	LENGTHS 1.80 mt and longer
Front faces	Back faces	THICKNESS 27 mm 33/34 mm 40 mm 52 mm 65 mm 80 mm 102 mm 120 mm	24 cm and wider	LENGTHS 1.80 mt and longer
Front faces	Back faces	THICKNESS 27 mm 33/34 mm 40 mm 52 mm 65 mm 80 mm 102 mm 120 mm	24 cm and wider	LENGTHS 1.80 mt and longer
Front faces	Back faces Description of the content of the con	THICKNESS 27 mm	WIDTHS 12 cm and wider allowing 10-11 cm	LENGTHS 1.80 mt and longer

Back faces

Super Prime

WIDTHS

LENGTHS



Pri-Fas



Natural



Rustic



SAP1F



NATURAL and RUSTIC are also available S2S (pre-planed) We produce this items also S2S pre-planed for companies that are using scanners to optimize (rip and/or cross cut) the boards and they prefer and need to have the wood pre-planed (clear from water stains or sticker marks). We are grading the material after the plaining. When S2S is very flat and straight.







Giorgio Marin S.p.a. Via Spada, 15 31050 Fanzolo di Vedelago Treviso - Italy Tel. +39 0423 487044 Fax +39 0423 476011 wood@maringiorgio.it www.maringiorgio.it